

# www.wotanforest.cz

Quality characteristics ALFA technic and ALFA joiner - coniferous plywood

		ALFA technic	- water - resis	tant plywood	ALFA joiner - joiner's plywood			
	quality class according producer	quality BB	quality C+	quality C	quality B	quality BB	quality C	
	quality class according EN 635-3	quality II. (BB)	quality III. (CP)	quality III. (C)	quality I. (B)	quality II. (BB)	quality III. (C)	
	sound knots	allowed up to Ø 50 mm	allowed up to Ø 60 mm	allowed up to Ø 60 mm	allowed up to Ø 5 mm	allowed up to Ø 5 mm	dovoleno do Ø 5 mm	
	unsound or partially fused knots	allowed up to Ø 10 mm	allowed up to Ø 40 mm puttied	allowed up to Ø 40 mm	allowed up to Ø 3 mm	allowed up to Ø 3 mm	allowed up to Ø 3 mm	
	knot holes	puttied and up Ø 5 mm not puttied	allowed up to Ø 40 mm puttied	allowed up to Ø 40 mm	not allowed	not allowed	allowed up to Ø 25 mm, max. 6 pcs/m²	
	knot holes machine repaired	allowed	allowed	allowed	allowed max. 3 patches/m²	allowed max. 6 patches/m²	allowed	
cts	open splits	allowed up to width 10 mm max. length 80 cm puttied	allowed up to width 10 mm max. length 80 cm puttied	allowed up to width 15 mm max. length 125 cm	not allowed	allowed up to width 3 mm max. 3 pcs per sheed width puttied	allowed up to width 5 mm max. 3 pcs per sheed width	
wood defects	bark or withered wood	allowed up to width 6 mm puttied	allowed up to width 6 mm puttied	allowed up to width 6 mm	not allowed	allowed up to width 3 mm and length 20 mm max. 2 pcs/m² puttied	allowed up to width 6 mm and length 20 mm max. 2 pcs/m²	
po	resin galls	allowed up to width 6 mm puttied	allowed up to width 40 mm puttied	allowed up to width 40 mm	not allowed	not allowed	allowed up to width 6 mm	
No.	soft rot	not allowed	not allowed	not allowed	not allowed	not allowed	not allowed	
	hard rot	not allowed	allowed	allowed	not allowed	not allowed	allowed	
	insect damage	allowed up to Ø 3 mm, 10 pcs/m² puttied	allowed up to Ø 5 mm, puttied	allowed up to Ø 5 mm	not allowed	not allowed	allowed up to Ø 5 mm, max.2 pcs/m²	
	natural stain	allowed up to 1/3 of sheed, no contrast	allowed up to 1/3 of sheed	allowed	allowed no contrast	allowed up to 1/3 of sheed	allowed	
	blue stain	allowed no contrast	allowed up to 1/3 of sheed	dovoleno	not allowed	not allowed	allowed	
S.	open joint	allowed up to 10 mm max. 1 pcs of sheet width, puttied	allowed up to 10 mm max. 1 pcs of sheet width, puttied	allowed up to 15 mm max. 1 pcs of sheet width	not allowed	allowed up to 3 mm max. 1 pcs of sheet width, puttied	allowed up to 5 mm max. 1 pcs of sheet width	
fec	overlap *)	not allowed	allowed 1 pcs/m², puttied	allowed max. 2 pcs/m²	not allowed	allowed max. 1 pcs/m² puttied	allowed max. 2 pcs/m²	
manufacturing defects	skim - dry mark (pressed in spots)	not allowed	allowed, max. width 40 mm, max. length 70 cm, 1 pcs of sheed width, puttied	allowed, max. width 40 mm, max. length 70 cm, 1 pcs of sheet width	not allowed	allowed max. 2 cm², up to max. depth 0,5 mm, puttied	allowed max. 2 cm², up to max. depth 0,5 mm	
urin	sanding through	not allowed	allowed light	allowed light	not allowed	not allowed	allowed light	
fact	rough spots	not allowed	allowed max. 10% of sheet	allowed	not allowed	allowed max. 10% of sheet	allowed	
ann	glue penetration **)	not allowed	allowed max. 10% of sheet	allowed	not allowed	allowed max. 2% of sheet	allowed	
Ε	manual repair	not allowed	allowed	allowed	not allowed	allowed	allowed	

<sup>\*)</sup> Overlaps of innerveneers are allower without restrictions.

### Functional characteristics ALFA technic - coniferous plywood

		characteristics according EN 13986: 2004 + A1: 2015								standard		
	thickness			4-6 mm	9 mm	12 mm	15 mm	18 mm	21 mm	24 mm	27+ mm	
	bending strenght	N/mm²	  -	28 11	27 11	33 20	28 14	30 19	25 19	27 10	26 22	EN 310 EN 326
	elastic modulus	N/mm²	  -	1300 950	3500 1200	4500 2700	4200 2300	5100 2500	4500 2600	4700 3100	5100 4500	EN 310
	bonding quality	N/mm² 0,6 - 1,0 bonding class 3 according EN 636-3									EN 314-1 EN 314-2	
	fire reaction	class D - s2, d0 applies to thicknesses from 9 mm and density higher than 400kg/m2								00kg/m2	EN 13986+A1 tab. 8	
à	release of formaldehyde	mg/m².h emission class E1 0,48							EN 636			
	formaldehyde content	mg HCHO/r ppm	g HCHO/m <sup>3</sup> chamber value 0,020 ppm ≤ 0,050							EN 717-1		
	water vapour permeability	μ	$\mu \hspace{1cm} \text{wet 70, dry 200}$							EN 12524		
	thermal conductivity	λ		0,13 W/mK							EN 12664	

### Quality characteristics ALFA floor - rotary cut spruce veneer

### ALFA floor - parquet veneer allowed up to 10 mm width and 1/4 length veneer, longitudinal cracks max. 1 pcs from every side closed cracks allowed up to 1/3 length veneer, max. 1 pcs from every side not allowed allowed up to 5 % veneer blue stain brown sap stain allowed up to 150 mm<sup>2</sup> not allowed resin galls allowed up to 150 mm<sup>2</sup> not allowed mechanical damaged not allowed insect damaged sound knots dead knots, unsound knots and decrements allowed up to Ø 20 mm allowed up to Ø 30 mm knots holes allowed up to height 50 mm 5-7%













<sup>\*\*)</sup> Board must be sanded. On not sanded board, traces of adhesive may appear on board surface.



# www.wotanforest.cz

## Thickness tolerances (ČSN EN 315)

	unsanded board				sanded board			
nominal thickness (mm)	number of plies (pcs)	min. (mm)	max. (mm)	in 1 board (mm)	number of plies (pcs)	min. (mm)	max. (mm)	in 1 board (mm)
4	3	3,5	4,9	1,0	3	3,5	4,3	0,6
5	3	4,5	6,0	1,0	3	4,5	5,4	0,6
6	3	5,4	7,0	1,0	3	5,4	6,4	0,6
8	5	7,4	9,0	1,0	5	7,4	8,4	0,6
9	5	8,3	10,1	1,0	5	8,3	9,5	0,6
10	5	9,3	11,1	1,0	5	9,3	10,5	0,6
12	5	11,2	13,2	1,0	5	11,2	12,6	0,6
15	5	14,2	16,3	1,5	7	14,2	15,7	0,6
18	7	17,1	19,3	1,5	7	17,1	18,7	0,6
21	7	20,0	22,4	1,5	9	20,0	21,8	0,6
24	9	22,9	25,5	1,5	9	22,9	24,9	0,6
27	11	25,8	28,6	1,5	11	25,3	28,6	0,8
30	11	28,7	31,7	1,5	11	28,1	31,7	0,8
veneer 2 mm		1,8 mm	2,2 mm					

Pac	

rackaging	
plywood thickness (mm)	pack height 900 mm (pcs/pack)
4	225
5	180
6	150
8	113
9	100
10	90
12	75
15	60
18	50
21	43
24	38
27	33
30	30
veneer thickness 2 mm	300

## Format tolerances (ČSN EN 315)

plywood length x width (mm)	maximal difference (mm)
2500×1250	+/-3,5
2440 x 1220	+/-3,5
2500×1500	+ / - 3,5
cut to size veneer	+10/-0

### Transport loading capacity 24 t

	number of packs	quantity (m³)		
plywood format 2500 x 1250 mm	17	48		
plywood format 2440 x 1220 mm	18	48		
plywood format 2500 x 1500 mm	12,5	42		
veneer format	36	40 (20 000 m²)		











